

Belzona 4181

FN10079

(AHR MAGMA-QUARTZ)



INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

Any surface to which **Belzona® 4181** is to be applied must be clean, firm and dry. Wash old concrete down with detergent to remove oil, grease and dust. Use clean water to wash away the detergent. Remove all paint, tar and any other coatings.

Allow new concrete to cure for a minimum of 28 days or until the moisture content is below 6% using a Protimeter.

Wire brush vertical upstands to remove loose surface material.

Horizontal concrete surfaces and new concrete will show the phenomenon of surface laitance and this must be removed by mechanical scarification.

Abrade metallic surfaces to remove loose rust and flaking paint and then roughen by blasting, grinding or other suitable means to achieve a rough bright metal surface. Vacuum up any loose dust produced by surface preparation techniques.

Treat any surface to which **Belzona® 4181** should not adhere with **Belzona® 9411** (Release Agent) and leave for 15 - 20 minutes to dry before proceeding; seal porous surfaces to be treated with **Belzona® 9411** first, with a suitable lacquer, e.g. shellac or cellulose enamel.

2. CONDITIONING

For application in chemical environments use **Belzona® 4911**. For applications involving elevated temperatures use **Belzona® 4981**.

BELZONA® 4911

Add the entire contents of **Belzona® 4911** (Magma TX Conditioner) Solidifier to **Belzona® 4911** Base and stir thoroughly until completely mixed. Immediately brush all of this conditioner onto the surface to be treated with **Belzona® 4181**, with a stiff bristled brush, not exceeding an area of 12 sq.ft. (1.1 m²) per 450g unit.

NOTES:

- For mixing small quantities of **Belzona® 4911** use:
2 Parts Base : 1 Part Solidifier by Volume
- Conditioning and overcoating must be completed within the following times:

Ambient Temperature	Usable life after mixing	Minimum overcoating time	Maximum overcoating time*
59°F/15°C	55 mins	Application can commence as soon as conditioning has been completed	6 hours
68°F/20°C	45 mins		6 hours
77°F/25°C	32 mins		6 hours

BELZONA® 4981

Add the entire contents of **Belzona® 4981** Solidifier to **Belzona® 4981** Base and stir thoroughly until completely mixed. Immediately brush all of this conditioner onto the surface to be treated with **Belzona® 4181**, with a stiff bristled brush, not exceeding an area of 75 sq.ft. (7 m²) per 3kg unit.

NOTES:

- For mixing small quantities of **Belzona® 4981** use:
3 Parts Base : 1 Part Solidifier by Volume
- Conditioning and overcoating must be completed within the following times:

Ambient Temperature	Usable life after mixing	Minimum overcoating time	Maximum overcoating time*
59°F/15°C	55 mins	Application can commence as soon as conditioning has been completed	4 hours
68°F/20°C	45 mins		4 hours
77°F/25°C	32 mins		4 hours

* If the maximum overcoating time for the **Belzona® 4911** or **Belzona® 4981** is exceeded, then the cured surface should be abraded and fresh Conditioner applied.

3. COMBINING THE REACTIVE COMPONENTS

- Add the entire contents of **Belzona® 4181** Solidifier to **Belzona® 4181** Base and stir thoroughly until completely mixed.
- Empty the entire contents into the large mixing bucket.
- Slowly add the **Belzona® 4181** Aggregate into the resin mix. Mix for 5 minutes and then proceed immediately to Section 4 "Application"

NOTES:

1. WORKING LIFE

From the commencement of mixing, **Belzona® 4181** must be used within the times shown below.

Temperature	Use all material within
59°F/15°C	45 mins
68°F/20°C	35 mins
77°F/25°C	30 mins

2. MIXING OF SMALL QUANTITIES

For mixing small quantities of **Belzona® 4181**, use:-
100 parts of Base to 30 parts of Solidifier to 1000 parts Aggregate by weight.

3. VOLUME CAPACITY OF MIXED BELZONA® 4181

6300 cm³ (384 cu.ins.) per 15 kg pack.

4. COVERAGE RATE

On a flat smooth surface, the coverage rate of **Belzona® 4181** is 10.67 sq.ft. at a thickness of 0.25 ins, (1.05m² at a thickness of 6 mm) per 15 kg pack

4. APPLYING BELZONA® 4181

Apply the mixed **Belzona® 4181** directly onto the conditioned surface, initially spreading to a general level using normal screeding techniques and then using a metal straight edge to achieve a uniform thickness prior to smoothing off using a steel float.

When a very smooth finish to the **Belzona® 4181** is required, this can be achieved by use of a steel float, cleaned and wetted with **Belzona® 9121**.

Complete the operation within 30 minutes (see .Working Life.) as after this time the **Belzona® 4181** will begin to solidify. When working with large volumes of **Belzona® 4181**, the usable life can be extended by spreading mixed material out on a board to avoid heat build-up during use.

NOTES:

1. APPLICATION TO VERTICAL SURFACES

When applying **Belzona® 4181** to vertical surfaces, the normal maximum thickness obtainable without sagging is 0.25 ins. (6 mm.). However, on small areas thicknesses of 0.5 ins. (12 mm.) can be achieved without sagging and, if necessary, a piece of polyethylene can be pressed onto the surface of the **Belzona® 4181** to prevent sagging. The polyethylene can be removed when the **Belzona® 4181** has cured.

2. APPLICATION LIMITS

Belzona® 4181 can be applied when the temperature of the material, substrate and environment is anywhere between 59°F (15°C) and 86°F (30°C). Below 59°F (15°C), the material will be too stiff for easy mixing and application. Above 86°F (30°C), the material may be somewhat fluid and will have a short usable life.

Reference must also be made to the cure times. Below 59°F (15°C), the rate of cure is drastically reduced and some external heat source must be used to effect full cure.

3. DAMP SURFACES

Belzona® 4181 can be applied to damp surfaces but its adhesion will be approximately 75% of that obtained on a dry surface.

4. APPLYING ADDITIONAL LAYERS OF BELZONA® 4181

Where this is required it should be done as soon as the first layer is firm enough to accept the second layer and within the maximum overcoating time of 6 hours.

After this time the surface of the **Belzona® 4181** must be abraded before further application.

In all cases the surface must be conditioned with either **Belzona® 4911** or **Belzona® 4981** (see Section 2) before applying further **Belzona® 4181**.

5. CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. Methyl ethyl ketone (MEK). Application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

5. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 4181** to solidify for the following times before subjecting it to the conditions indicated:

Temperature	59°F (15°C)	77°F (25°C)
To resist pedestrian traffic	12 hours	8 hours
Machine hard	16 hours	12 hours
For full mechanical hardness	48 hours	24 hours
For full chemical resistance	10 days	5 days

These figures are for **Belzona® 4181** at a film thickness of 0.25 ins. (6 mm). They will be reduced for higher film thicknesses.

6. STORAGE & TRANSPORTATION

Prolonged storage of **Belzona® 4181** Solidifier below 50°F (10°C) may result in partial solidification. If this occurs, the material can be restored to its normal form by resealing the container and warming to between 104°F (40°C) and 122°F (50°C) for 3 hours in a well ventilated, dry area.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2025 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

